

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of :

Martin HEENEY et al.

Serial No. : Unassigned

Filed : April 16, 2004

For : A PROCESS OF PREPARING A DISUBSTITUTED 9-
ALKYLIDENEFLUORENE OR A DERIVATIVE THEREOF

SUBMISSION OF PRIORITY DOCUMENT(S)

Commissioner for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

Sir:

Submitted herewith is a certified copy of each of the below-identified document(s),
benefit of priority of each of which is claimed under 35 U.S.C. § 119:

COUNTRY	APPLICATION NO.	FILING DATE
GERMANY	03008726.6	April 16, 2003

Acknowledgment of the receipt of the above document(s) is requested.

No fee is believed to be due in association with this filing, however, the Commissioner is
hereby authorized to charge fees under 37 C.F.R. §§ 1.16 and 1.17 which may be required to
facilitate this filing, or credit any overpayment to Deposit Account No. 13-3402.

Respectfully submitted,

James E. Ruland, Reg. No. 37,432
Attorney for Applicants

MILLEN, WHITE, ZELANO
& BRANIGAN, P.C.
Arlington Courthouse Plaza 1
2200 Clarendon Blvd. Suite 1400
Arlington, Virginia 22201
Telephone: (703) 243-6333
Facsimile: (703) 243-6410

Attorney Docket No.: MERCK-2679

Date: April 16, 2004

K:\Merck\2679\Submission of Priority Documents.doc

THIS PAGE BLANK (USPTO)



**Europäisches
Patentamt**

**European
Patent Office**

**Office européen
des brevets**

Bescheinigung

Certificate

Attestation

Die angehefteten Unterlagen stimmen mit der ursprünglich eingereichten Fassung der auf dem nächsten Blatt bezeichneten europäischen Patentanmeldung überein.

The attached documents are exact copies of the European patent application described on the following page, as originally filed.

Les documents fixés à cette attestation sont conformes à la version initialement déposée de la demande de brevet européen spécifiée à la page suivante.

Patentanmeldung Nr. Patent application No. Demande de brevet n°

03008726.6

Der Präsident des Europäischen Patentamts;
Im Auftrag

For the President of the European Patent Office

Le Président de l'Office européen des brevets
p.o.

R C van Dijk

THIS PAGE BLANK (USPTO)



Anmeldung Nr:
Application no.: 03008726.6
Demande no:

Anmeldetag:
Date of filing: 16.04.03
Date de dépôt:

Anmelder/Applicant(s)/Demandeur(s):

MERCK PATENT GmbH
Frankfurter Strasse 250
64293 Darmstadt
ALLEMAGNE

Bezeichnung der Erfindung/Title of the invention/Titre de l'invention:
(Falls die Bezeichnung der Erfindung nicht angegeben ist, siehe Beschreibung.
If no title is shown please refer to the description.
Si aucun titre n'est indiqué se référer à la description.)

Process of preparing disubstituted 9-alkylidene fluorenes and derivatives thereof

In Anspruch genommene Priorität(en) / Priority(ies) claimed / Priorité(s)
revendiquée(s)
Staat/Tag/Aktenzeichen/State/Date/File no./Pays/Date/Numéro de dépôt:

Internationale Patentklassifikation/International Patent Classification/
Classification internationale des brevets:

C07D333/00

Am Anmeldetag benannte Vertragsstaaten/Contracting states designated at date of
filing/Etats contractants désignées lors du dépôt:

AT BE BG CH CY CZ DE DK EE ES FI FR GB GR HU IE IT LU MC NL
PT RO SE SI SK TR LI

THIS PAGE BLANK (USPTO)

EPO - Munich
67
16 April 2003

**Merck Patent Gesellschaft
mit beschränkter Haftung
64271 Darmstadt**

**Process of Preparing Disubstituted 9-
Alkylidenefluorenes and Derivatives thereof**

Process of Preparing Disubstituted 9-Alkylidene fluorenes and Derivatives thereof

Field of Invention

5

The invention relates to a process of preparing disubstituted 9-alkylidene fluorenes and structure analogous compounds, and to novel compounds and intermediates prepared by this process. The invention further relates to the use of the compounds obtainable by the process for the preparation of conjugated polymers and copolymers thereof, and to novel polymers and copolymers thereby prepared. The invention further relates to use of the compounds and polymers as semiconductors or charge transport materials in optical, electrooptical or electronic devices including field effect transistors, electroluminescent, photovoltaic and sensor devices. The invention further relates to field effect transistors and semiconducting components comprising the novel compounds and polymers.

10

15

Background and Prior Art



20

It is known in prior art that alkylidene fluorene (1) and poly(9-alkylidene fluorene) (2) are suitable for use as semiconductor and charge transport materials. These materials exhibit a high degree of planarity in the backbone due to the carbon sp^2 hybridisation at the 9 position, in comparison with for example poly(9,9-dialkyl fluorenes), and strong interchain pi-pi-stacking interactions, making them effective charge transport materials with high carrier mobilities. In addition, the high resonance stability of the fused phenylene structure leads to a high ionisation potential and hence good stability. Also, the incorporation of alkyl substituents R^1 , R^2 into the alkylidene fluorene group leads to good solubility and thus good solution processibility of the materials according to the present invention. Solution processing during device manufacture has the advantage over vacuum deposition of being a potentially cheaper and faster technique.

25

30

35



US 6,169,163 discloses monosubstituted 9-alkylidene fluorenes (1) and poly(9-alkylidene fluorenes) (2) ($R^1 = \text{alkyl}$, $R^2 = \text{H}$). Copolymers of disubstituted 9-alkylidene fluorenes ($R^1 = R^2 = \text{alkyl}$ optionally substituted) are disclosed in WO 00/46321, although no example or method for the preparation of monomer (1) is disclosed. The synthesis of specific monosubstituted 9-alkylidene fluorenes (1) ($R^1 = \text{alkyl}$, $R^2 = \text{H}$) is also described in K. Subba Reddy et al., *Synthesis*, 2000, 1, 165.

The synthesis of specific disubstituted 9-alkylidene fluorenes (1) ($R^1 = \text{methyl}$, $R^2 = \text{methyl or phenyl}$) is disclosed in K. C. Gupta et al., *Indian J. Chem., Sect. B*, 1986, 25B, 1067. This involves a Wittig type reaction between a 9-fluorenyl- phosphonium or phosphate salt and a ketone. The main drawback of this method, however, is the necessity to synthesise the starting Wittig reagent, and the expense and lack of availability of aliphatic ketones.

The synthesis of a specific copolymer of disubstituted 9-alkylidene-fluorene (1) ($R^1 = \text{methyl}$, $R^2 = \text{ethyl}$) is reported by M. Ranger and M. Leclerc, *Macromolecules* 1999, 32, 3306. According to this reference, the monomers (1) are prepared by the reaction of a secondary Grignard reagent with 2,7-dibromofluorenone, followed by dehydration of the resulting tertiary alcohol. However, this route is limited by the paucity of secondary Grignard reagents that are available.

Moreover, the methods of preparing disubstituted 9-alkylidene-fluorenes as disclosed in the above references of Gupta et al. and Ranger et al. are not readily amenable to the preparation of molecules with alkyl chains larger than propyl. Also, polymers of unsymmetrical 9-alkylidene fluorenes as disclosed in these


references have the general problem of poor regioregularity and therefore poor ordering and packing in the solid state.

5 EP 1 284 258 A2 discloses novel mono-, oligo- and polymers of disubstituted 9-alkylidene-fluorene. It also discloses a synthesis method that overcomes the problems outlined above by describing a new 3-step synthetic procedure for the preparation of monomers (1), as well as procedures for the preparation of polymers and co-polymers derived from (1). However, the reaction yields and reaction
10 times of this method do still leave room for further improvement.

It was an aim of the present invention to provide an improved process for preparing disubstituted 9-alkylidene-fluorene or structure
15 analogous compounds, and oligo- or (co)polymers thereof.

Other aims of the present invention are immediately evident to the person skilled in the art from the following detailed description.

It was found that these aims can be achieved by a process of
20 preparing disubstituted 9-alkylidene-fluorenes according to the present invention as described below. In particular, this invention describes an improved process for the preparation of monomers (1) which has improved yields and reduced reactions times. It was also found that the process according to the present invention can be used to prepare
25 aromatic compounds which are structure-analogous to 9-alkylidene-fluorene (1), like for example 4-alkylidenecyclopentadithiophenes (3).




35 The compounds prepared by the process according to the present invention are especially useful for the preparation of oligo- and

polymers or copolymers, like e.g. poly(9-alkylidenefluorenes), which are suitable as charge transport materials for semiconductor or light-emitting materials, components or devices.

5 Summary of the Invention

The invention relates to a process of preparing a compound of formula I

10




15

by

a) reacting a compound of formula Ia

20




Ia

25

with a base in the presence of carbondisulfide or a dialkyl trithiocarbonate of the formula [(R'S)₂CS] and an alkylating agent (R'X), and

b) reacting the resulting compound of formula Ib

30



Ib

35

with a Grignard reagent R^1MgX and/or R^2MgX in the presence of a copper catalyst,

wherein

5

A^1 and A^2 are independently of each other an aromatic 5-, 6- or 7-membered ring which optionally contains one or more hetero atoms and is optionally substituted with one or more identical or different groups R,

10

R is halogen or has one of the meanings of R^1 ,

15

R^1 and R^2 are independently of each other straight chain, branched or cyclic alkyl with 1 to 20 C-atoms, which may be unsubstituted, mono- or poly-substituted by F, Cl, Br, I or CN, it being also possible for one or more non-adjacent CH_2 groups to be replaced, in each case independently from one another, by -O-, -S-, -NH-, - NR^0 -, - SiR^0R^{00} -, -CO-, -COO-, -OCO-, -OCO-O-, - SO_2 -, -S-CO-, -CO-S-, -CH=CH- or -C \equiv C- in such a manner that O and/or S atoms are not linked directly to one another, optionally substituted aryl or heteroaryl, or P-Sp,

20

25

R^0 and R^{00} are independently of each other H or alkyl with 1 to 12 C-atoms,

P is a polymerisable or reactive group,

30

Sp is a spacer group or a single bond,

X is halogen, and


35

R' is straight, branched or cyclic alkyl with 1 to 20 C-atoms, which may be unsubstituted, mono- or poly-substituted by F, Cl, Br, I or CN, it being also possible for one or more non-adjacent CH_2 groups to be replaced, in each

- 6 -

case independently from one another, by -O-, -S-, -NH-,
 -NR⁰-, -SiR⁰R⁰⁰-, -CO-, -COO-, -OCO-, -OCO-O-, -SO₂-,
 -S-CO-, -CO-S-, -CH=CH- or -C≡C- in such a manner
 that O and/or S atoms are not linked directly to one
 another, or alkyl aryl with up to 20 C-atoms.


More specifically, the invention relates to a process of preparing a
 compound of formula I1



I1

by


a) reacting a compound of formula I1a



I1a

with a base in the presence of carbondisulfide or a dialkyl
 trithiocarbonate of the formula [(R'S)₂CS] and an alkylating agent
 (R'X), and

b) reacting the resulting compound of formula I1b




10 with a Grignard reagent R^1MgX and/or R^2MgX in the presence of a copper catalyst,

wherein R^1 , R^2 , R' and X have the meanings given above,


15 R^3 to R^{10} are independently of each other H or have one of the meanings given for R , wherein at least one of R^3 to R^8 , preferably R^9 and R^{10} , are independently of each other halogen.

20 Furthermore, the invention relates to a process of preparing a compound of formula I2




by

30 a) reacting a compound of formula I2a



with a base in the presence of carbondisulfide or a dialkyl trithiocarbonate of the formula $[(R'S)_2CS]$ and an alkylating agent $(R'X)$, and

5 b) reacting the resulting compound of formula I2b



with a Grignard reagent R^1MgX and/or R^2MgX in the presence of a copper catalyst,

15 wherein R^{1-4} , R' and X have the meanings given above, and R^9 and R^{10} are preferably independently of each other H or halogen.

The invention further relates to novel compounds and intermediates, in particular novel compounds of formula I, I1, I2, I1a, I1b, I2a and I2b, obtainable or obtained by the process or used in the process as described above and below.

Detailed Description of the Invention

25 The process according to the present invention offers significant advantages over the methods disclosed in prior art in terms of yield, number of reaction steps and synthetic flexibility. Thus for example various groups R^1 and R^2 can be readily incorporated. In particular, the process according to the present invention enables high yields and fast reaction times. In particular, the use of a copper catalyst has the advantage of lowering the reaction temperature, from reflux to temperatures down to 0°C , reducing the amount of alkyl grignard used, e.g. from 2.5 equivalents down to 2.2 equivalents, improving the yield and reducing the amount of byproducts, thereby aiding purification. In contrast, for example the use of Ni or Pd catalysts has


30

35

the disadvantage that they can also catalyse the displacement of the bromine groups on the fluorene core.


The two-step process according to the present invention is exemplarily shown in Scheme 1 below. The first step involves the reaction of 2,7-dihalofluorene, preferably 2,7-dibromofluorene (**4**), which is a cheap and readily available starting material, with a base in the presence of carbon disulfide (CS_2) and an alkylating agent ($\text{R}'\text{X}$). This affords the dithioalkyl substituted fluorene (**5**) directly in one step. Alternatively to CS_2 a dialkyl trithiocarbonate of the formula $[(\text{R}'\text{S})_2\text{CS}]$ can be used, wherein R' is as defined above. In this case the alkylating agent ($\text{R}'\text{X}$) and the dialkyl trithiocarbonate $[(\text{R}'\text{S})_2\text{CS}]$ should comprised the same group R' (for example methyl). The alkylating agent $\text{R}'\text{X}$ can be any primary alkyl or alkyl aryl halide. X is for example Cl , Br or I , preferably Br . R' is for example an alkyl or alkyl aryl group like methyl, hexyl or benzyl. (**5**) is then reacted with a Grignard reagent R^1MgX , wherein R^1 and X are as defined above, in the presence of a copper catalyst like for example Li_2CuCl_4 , to form the disubstituted 9-alkylidenefluorene (**6**).

Scheme 1:



The preparation of structure analogous compounds, like for example 4-alkylidenecyclopentadithiophenes, is carried out in analogy to the above described process, and is exemplarily shown in Scheme 2 below. 2,6-Dibromocyclopentadienethiophene (7) is reacted with a base in the presence of carbon disulfide and an alkylating agent (R'X) to afford the dithioalkyl substituted compound (8), which is reacted with a Grignard reagent R¹MgX in the presence of a copper catalyst like for example Li₂CuCl₄ to form the disubstituted 4-alkylidenecyclopentadienethiophene (9).

Scheme 2:



The starting materials and reagents used in the process according to the present invention are either commercially available (e.g. from Aldrich) or can be easily synthesized by methods well known to those skilled in the art.

Step a) of the inventive process is carried out in the presence of carbondisulfide (CS₂) or, more preferably, in the presence of a dialkyltrithiocarbonate of the formula [(R'S)₂CS]. Therein, R' is preferably selected from methyl, ethyl or propyl, very preferably methyl.

- 5 The alkylating agent in step a) can be any alkylating agent, like for example an alkylhalogenide or alkyl aryl halogenide. Preferably it is selected of formula $R'X$, wherein X is halogen, preferably Cl, Br or I, very preferably Br or I, and R' is alkyl or alkyl aryl with 1 to 15 C-atoms. Very preferably it is selected from methyl iodide, ethyl bromide, propyl bromide, hexyl bromide or benzyl bromide, most preferably from methyl iodide, ethyl bromide or benzyl bromide. If a dialkyltrithiocarbonate of the formula $[(R'S)_2CS]$ is used in step a) then both groups R' should preferably be identical.
- 10 The base in step a) can principally any base of sufficient strength. Preferably it is selected from NaH, NaOtBut, KOtBut, KOH, NaOH, NaOMe, NaOEt, NaOtPent, KOtPent, very preferably from NaH, NaOtBut, KOtBut, or KOH.
- 15 Reaction step a) is preferably carried out in a dipolar aprotic solvent, which can be any solvent of this type, like for example DMSO, DMF, DMPU, DMAc or NMP.
- 20 The copper catalyst in step b) can be any catalyst that is suitable for a reaction involving organometallic reagents, and is preferably selected from CuI, CuBr or Li_2CuCl_4 , most preferably Li_2CuCl_4 .
- 25 The Grignard reagent in step b) can be any Grignard reagent, and is preferably of formula R^1MgX wherein X is Cl, Br or I, preferably Br or Cl. Preferably the Grignard reagent in step b) is added in an amount of from 2 to 3, very preferably 2 to 2.4, most preferably 2 to 2.2 equivalents of the thioalkyl substituted compound Ib, I1b or I2b, respectively.
- 30 Reaction step b) is preferably carried out in a polar aprotic solvent, which can be any solvent of this type, like for example THF, diethyl ether, dioxane, 1,2-dimethoxyethane or tertbutylmethylether.
- 35 The process according to the present invention may be run at any temperature providing a sufficient conversion rate. It is preferred that

the reaction is performed at a temperature between 0 °C and the solvent's reflux temperature, in particular at the temperatures as specified above and below. The reaction time depends on the actual rate of the individual reaction.

5

Preferably the reaction times are as given above and below.

10

For step a) the reaction temperature is preferably between 10°C and 100°C, most preferably between 15°C and 40°C. The reaction time is between 15 min and 24 h, most preferably between 30 min and 4 h. For step b) the reaction temperature is between -5°C and reflux, most preferably between 0°C and 30°C. The reaction times are between 3h and 48 h, preferably between 3h and 24h.

15

20

The reaction products prepared by process according to the present invention may be isolated by usual work-up and purification with standard procedures well known to those skilled in the art. The crude product obtained in step a) can be directly used in step b) or can be purified before further reaction. The products obtained in step b) can be purified by known methods, or may also be used without further purification, for example for the preparation of polymers or copolymers.

25

Preferably, the process according to the present invention is carried out as follows:

Step a):

30

35

Dibromofluorene (3) or 2,6-dibromocyclopentadiene-thiophene (7) is dissolved in a dipolar aprotic solvent, like for example, DMSO, DMF or DMAc and stirred at room temperature (RT) or close to RT, for example 25°C, under an dry atmosphere, e.g. under nitrogen or dried air. More than 2 equivalents, preferably 2.1 equivalents, of base are added portionwise or as a solution in said solvent. Suitable and preferred bases include for example NaH, sodium tert-butoxide, finely ground KOH and potassium tert-butoxide. After stirring the

reaction mixture for approximately 10 minutes, carbon disulfide or dimethyl trithiocarbonate (MeS)₂CS are added as neat liquids. Dimethyl trithiocarbonate is preferred over carbon disulfide because the latter has a flash point below 200°C, which can make larger scale processing problematic. The resulting solution is stirred for approximately 15 minutes, and then the alkylating agent, for example methyl iodide, ethyl bromide or benzyl bromide, is added neat. The reaction is stirred at RT for 1h and then poured into water, and the resulting precipitate filtered to afford the crude product (>95%). The product can be recrystallised from THF for example or dried and used crude in the next step.

Step b):

Compound (5) or (7) is dissolved in THF, or an equivalent solvent like for example DME, diethyl ether etc.; and cooled to 0°C under an inert gas atmosphere of e.g. nitrogen. A solution of the copper catalyst, preferably Li₂CuCl₄, in a suitable solvent, like for example THF (preferably 3 mol % of a 0.1 M solution), is added, followed by more than 2, preferably 2.2 equivalents of a solution of alkyl or aryl Grignard reagent in THF or diethyl ether, in a concentration of typically 0.5 to 2M or more. The reaction is stirred for 4h at 0°C. The reaction is quenched with dilute sodium hydroxide solution (preferably 5%), filtered, and extracted in THF or ethyl acetate. The solvent is removed under reduced pressure and the resulting solid recrystallised from a suitable solvent (for example petrol) to afford (6) or (9), respectively, with a yield of typically 60-80%.

Especially preferred are compounds of formula I, I1 and I2 wherein

- A¹ and A² are an aromatic 5-ring or 6-ring that optionally contains one or two hetero atoms selected from N, O and S,
- A¹ and A² are selected from benzene, thiophene or pyridine.
- R¹ and R² are identical (these can be obtained by using a single Grignard reagent R¹MgX or R²MgX in step b),

- R^1 and R^2 are different (these can be obtained by using a mixture of two Grignard reagents R^1MgX and R^2MgX in step b),
- R^1 and R^2 are selected from C_1 - C_{20} -alkyl that is optionally substituted with one or more fluorine atoms, C_1 - C_{20} -alkenyl, C_1 - C_{20} -alkynyl, C_1 - C_{20} -alkoxy, C_1 - C_{20} -thioalkyl, C_1 - C_{20} -silyl, C_1 - C_{20} -ester, C_1 - C_{20} -amino, C_1 - C_{20} -fluoroalkyl, or optionally substituted aryl or heteroaryl, in particular C_1 - C_{20} -alkyl or C_1 - C_{20} -fluoroalkyl,
- R^3 to R^8 are H,
- R^1 and R^2 are selected from C_1 - C_{20} -alkyl that is optionally substituted with one or more fluorine atoms, C_1 - C_{20} -alkenyl, C_1 - C_{20} -alkynyl, C_1 - C_{20} -alkoxy, C_1 - C_{20} -thioalkyl, C_1 - C_{20} -silyl, C_1 - C_{20} -ester, C_1 - C_{20} -amino, C_1 - C_{20} -fluoroalkyl, or optionally substituted aryl or heteroaryl, in particular C_1 - C_{20} -alkyl or C_1 - C_{20} -fluoroalkyl, and R^3 to R^8 are H,
- R^3 to R^8 are selected from C_1 - C_{20} -alkyl that is optionally substituted with one or more fluorine atoms, C_1 - C_{20} -alkenyl, C_1 - C_{20} -alkynyl, C_1 - C_{20} -alkoxy, C_1 - C_{20} -thioalkyl, C_1 - C_{20} -silyl, C_1 - C_{20} -ester, C_1 - C_{20} -amino, C_1 - C_{20} -fluoroalkyl, and optionally substituted aryl or heteroaryl,
- R^9 and R^{10} are Cl, Br or I, very preferably Br.

Aryl and heteroaryl preferably denote a mono-, bi- or tricyclic aromatic or heteroaromatic group with up to 25 C atoms that may also comprise condensed rings and is optionally substituted with one or more groups R^1 as defined in formula I.

Especially preferred aryl and heteroaryl groups are phenyl in which, in addition, one or more CH groups may be replaced by N, naphthalene, thiophene, thienothiophene, dithienothiophene, alkyl fluorene and oxazole, all of which can be unsubstituted, mono- or polysubstituted with L, wherein L is halogen or an alkyl, alkoxy, alkylcarbonyl or alkoxycarbonyl group with 1 to 12 C atoms, wherein one or more H atoms may be replaced by F or Cl.

Arylene and heteroarylene preferably denote a bivalent mono-, bi- or tricyclic aromatic or heteroaromatic group with up to 25 C atoms that may also comprise condensed rings and is optionally substituted with one or more groups R¹.

5

Especially preferred arylene and heteroarylene groups are 1,4-phenylene in which, in addition, one or more CH groups may be replaced by N, naphthalene-2,6-diyl, thiophene-2,5-diyl, thienothiophene-2,5-diyl, dithienothiophene-2,6-diyl, alkyl fluorene and oxazole; all of which can be unsubstituted, mono- or polysubstituted with L as defined above.

10

CX¹=CX² is preferably -CH=CH-, -CH=CF-, -CF=CH-, -CF=CF-, -CH=C(CN)- or -C(CN)=CH-.

15

If in the formulae shown above and below one of R¹ to R⁸ is an alkyl or alkoxy radical, i.e. where the terminal CH₂ group is replaced by -O-, this may be straight-chain or branched. It is preferably straight-chain, has 2 to 8 carbon atoms and accordingly is preferably ethyl, propyl, butyl, pentyl, hexyl, heptyl, octyl, ethoxy, propoxy, butoxy, pentoxy, hexyloxy, heptoxy, or octoxy, furthermore methyl, nonyl, decyl, undecyl, dodecyl, tridecyl, tetradecyl, pentadecyl, nonoxy, decoxy, undecoxy, dodecoxy, tridecoxy or tetradecoxy, for example.

20

25

Oxaalkyl, i.e. where one CH₂ group is replaced by -O-, is preferably straight-chain 2-oxapropyl (=methoxymethyl), 2- (=ethoxymethyl) or 3-oxabutyl (=2-methoxyethyl), 2-, 3-, or 4-oxapentyl, 2-, 3-, 4-, or 5-oxahexyl, 2-, 3-, 4-, 5-, or 6-oxaheptyl, 2-, 3-, 4-, 5-, 6- or 7-oxaoctyl, 2-, 3-, 4-, 5-, 6-, 7- or 8-oxanonyl or 2-, 3-, 4-, 5-, 6-, 7-, 8- or 9-oxadecyl, for example.

30

Thioalkyl, i.e. where one CH₂ group is replaced by -S-, is preferably straight-chain thiomethyl (-SCH₃), 1-thioethyl (-SCH₂CH₃), 1-thiopropyl (= -SCH₂CH₂CH₃), 1- (thiobutyl), 1-(thiopentyl), 1- (thiohexyl), 1-(thioheptyl), 1-(thiooctyl), 1-(thiononyl), 1-(thiodecyl), 1-



35

(thioundecyl) or 1-(thiododecyl), wherein preferably the CH_2 group adjacent to the sp^2 hybridised vinyl carbon atom is replaced.


5 Fluoroalkyl is preferably $\text{C}_i\text{F}_{2i+1}$, wherein i is an integer from 1 to 15, in particular CF_3 , C_2F_5 , C_3F_7 , C_4F_9 , C_5F_{11} , C_6F_{13} , C_7F_{15} or C_8F_{17} , very preferably C_6F_{13} .

Halogen is preferably F, Br or Cl.

10 The polymerisable or reactive group P is preferably selected from

15 $\text{CH}_2=\text{CW}^1\text{-COO-}$, W^2HC  CH- , W^2  $(\text{CH}_2)_{k1}\text{-O-}$, $\text{CH}_2=\text{CW}^2\text{-(O)}_{k1}\text{-}$, $\text{CH}_3\text{-CH=CH-O-}$, $\text{HO-CW}^2\text{W}^3\text{-}$, $\text{HS-CW}^2\text{W}^3\text{-}$, $\text{HW}^2\text{N-}$, $\text{HO-CW}^2\text{W}^3\text{-NH-}$, $\text{CH}_2=\text{CW}^1\text{-CO-NH-}$, $\text{CH}_2=\text{CH-(COO)}_{k1}\text{-Phe-(O)}_{k2}\text{-}$, Phe-CH=CH- , HOOC- , OCN- and $\text{W}^4\text{W}^5\text{W}^6\text{Si-}$, with W^1 being H, Cl, CN, phenyl or alkyl with 1 to 5 C-atoms, in particular H, Cl or CH_3 , W^2 and W^3 being independently of each other H or alkyl with 1 to 5 C-atoms, in particular methyl, ethyl or n-propyl, W^4 , W^5 and W^6 being independently of each other Cl, oxaalkyl or oxacarbonylalkyl with 1 to 5 C-atoms, Phe being 1,4-phenylene and k_1 and k_2 being independently of each other 0 or 1.

25 Especially preferred groups P are $\text{CH}_2=\text{CH-COO-}$, $\text{CH}_2=\text{C(CH}_3\text{)-}$

COO- , $\text{CH}_2=\text{CH-}$, $\text{CH}_2=\text{CH-O-}$ and W^2  $(\text{CH}_2)_{k1}\text{-O-}$.

30 Very preferred are acrylate and oxetane groups. Oxetanes produce less shrinkage upon polymerisation (cross-linking), which results in less stress development within films, leading to higher retention of ordering and fewer defects. Oxetane cross-linking also requires cationic initiator, which unlike free radical initiator is inert to oxygen.

35 As for the spacer group Sp all groups can be used that are known for this purpose to the skilled in the art. The spacer group Sp is preferably of formula Sp'-X , such that P-Sp- is P-Sp'-X'- , wherein

Sp' is alkylene with up to 30 C atoms which is unsubstituted or mono- or polysubstituted by F, Cl, Br, I or CN, it being also possible for one or more non-adjacent CH₂ groups to be replaced, in each case independently from one another, by -O-,
 5 -S-, -NH-, -NR⁰-, -SiR⁰R⁰⁰-, -CO-, -COO-, -OCO-, -OCO-O-, -SCO-, -CO-S-, -CH=CH- or -C≡C- in such a manner that O and/or S atoms are not linked directly to one another,

10 X' is -O-, -S-, -CO-, -COO-, -OCO-, -O-COO-, -CO-NR⁰-, -NR⁰-CO-, -OCH₂-, -CH₂O-, -SCH₂-, -CH₂S-, -CF₂O-, -OCF₂-, -CF₂S-, -SCF₂-, -CF₂CH₂-, -CH₂CF₂-, -CF₂CF₂-, -CH=N-, -N=CH-, -N=N-, -CH=CR⁰-, -CY¹=CY²-, -C≡C-, -CH=CH-COO-, -OCO-CH=CH- or a single bond, and

15

R⁰, R⁰⁰, Y¹ and Y² have one of the meanings given above.

X' is preferably -O-, -S-, -OCH₂-, -CH₂O-, -SCH₂-, -CH₂S-, -CF₂O-, -OCF₂-, -CF₂S-, -SCF₂-, -CH₂CH₂-, -CF₂CH₂-, -CH₂CF₂-, -CF₂CF₂-, -CH=N-, -N=CH-, -N=N-, -CH=CR⁰-, -CX¹=CX²-, -C≡C- or a single bond, in particular -O-, -S-, -C≡C-, -CX¹=CX²- or a single bond. In another preferred embodiment X' is a group that is able to form a conjugated system, such as -C≡C- or -CX¹=CX²-, or a single bond.

25 Typical groups Sp' are, for example, -(CH₂)_p-, -(CH₂CH₂O)_q-CH₂CH₂-, -CH₂CH₂-S-CH₂CH₂- or -CH₂CH₂-NH-CH₂CH₂- or -(SiR⁰R⁰⁰-O)_p-, with p being an integer from 2 to 12, q being an integer from 1 to 3 and R⁰ and R⁰⁰ having the meanings given above.

30 Preferred groups Sp' are ethylene, propylene, butylene, pentylene, hexylene, heptylene, octylene, nonylene, decylene, undecylene, dodecylene, octadecylene, ethyleneoxyethylene, methyleneoxybutylene, ethylene-thioethylene, ethylene-N-methyl-iminoethylene, 1-methylalkylene, ethenylene, propenylene and
 35 butenylene for example.

Further preferred are compounds with one or two groups P-Sp- wherein Sp is a single bond.

5 In case of compounds with two groups P-Sp, each of the two polymerisable groups P and the two spacer groups Sp can be identical or different.

10 Another aspect of the invention is the use of compounds of formula I, I1 and I2 for the preparation of mono-, oligo- and polymers or copolymers thereof, in particular conjugated oligo- and (co)polymers.

15 Another aspect of the invention are mono-, oligo- and polymers or copolymers thereof, in particular conjugated oligo- and (co)polymers, obtainable from compounds of formula I, I1 and I2.

Oligo- and polymers can be prepared from the compounds of formula I, I1 and I2 by the methods as described in EP 1 284 258 A2 or the references cited therein.

20 Another aspect of the invention is a semiconductor or charge transport material, component or device comprising one or more compounds of formula I, I1 and I2 and mono-, oligo- and polymers or copolymers thereof, in particular conjugated oligo- and (co)polymers prepared thereof.

25 Another aspect of the invention is the use of compounds of formula I, I1 and I2 and mono-, oligo- and polymers or copolymers thereof, as semiconductors or charge transport materials, in particular in optical, electrooptical or electronic devices, like for example in field effect
30 transistors (FET) as components of integrated circuitry, as thin film transistors in flat panel display applications or for Radio Frequency Identification (RFID) tags, or in semiconducting components for organic light emitting diode (OLED) applications such as electroluminescent displays or backlights of e.g. liquid crystal
35 displays (LCD), for photovoltaic or sensor devices, as electrode

materials in batteries, as photoconductors and for electrophotographic applications like electrophotographic recording.

5 Another aspect of the invention is the use of the compounds or mono-, oligo- or (co)polymers according to the invention as electroluminescent materials, in photovoltaic or sensor devices, as electrode materials in batteries, as photoconductors, for electrophotographic applications like electrophotographic recording and as alignment layer in LCD or OLED devices.

10 Another aspect of the invention is an optical, electrooptical or electronic device, FET, integrated circuit (IC), TFT, OLED or alignment layer comprising a semiconducting or charge transport material, component or device according to the invention.

15 Another aspect of the invention is a TFT or TFT array for flat panel displays, radio frequency identification (RFID) tag, electroluminescent display or backlight comprising a semiconducting or charge transport material, component or device or a FET, IC, TFT
20 or OLED according to the invention.

Another aspect of the invention is a security marking or device comprising a FET or an RFID tag according to the invention.

25 The examples below serve to illustrate the invention without limiting it. In the foregoing and the following, all temperatures are given in degrees Celsius, and all percentages are by weight, unless stated otherwise.

30 Example 1:

Preparation of 2,7-dibromo-9-(bis-methylsulfanyl-methylene)fluorene (by reaction with carbon disulfide):

35 Sodium tert-butoxide (31.1g, 0.32 mol) was added portionwise over 5 min to a solution of 2,7-dibromofluorene (50g, 0.154 mol) in DMSO

(1000 ml) at RT (22°C) under nitrogen. To the resulting red solution was added carbon disulfide (13 g, 0.17 mol) via a syringe causing an exotherm to 35°C. The reaction was stirred for 10 min until the internal temperature was 30°C. Methyl iodide (46g, 0.32 mol) was added over 2 min, causing an exotherm to 42°C. The reaction was stirred for 1 h and quenched by the addition of ice water (1000 ml) and conc. ammonia (20 ml). The reaction was stirred for 10 min and then filtered under reduced pressure and washed with further water (500 ml). After drying the crude yield was 64.8 g (98%, purity (HPLC) 97.8%). Recrystallisation from ethyl acetate/ THF (2:1) afforded 55.2 g (purity (HPLC) 99.2%).): ^1H and ^{13}C NMR spectra as expected; $\text{M}^+ = 428$ (t). Anal. Calcd. For $\text{C}_{16}\text{H}_{12}\text{Br}_2\text{S}_2$: C, 44.9; H, 2.8, N, 0.0. Found C, 44.7, H, 3.1, N, <0.3.

Example 2:

Preparation of 2,7-dibromo-9-(bis-methylsulfanyl-methylene)fluorene (by reaction with dimethyl trithiocarbonate):

Sodium tert-butoxide (1.24g, 12.9 mmol) was added portionwise over 2 min to a solution of 2,7-dibromofluorene (2.0g, 6.2 mmol) in DMSO (40 ml) at RT under nitrogen. To the resulting red solution was added dimethyl trithiocarbonate (0.94 g, 6.8 mmol) via a syringe. The reaction was stirred for 5 min and methyl iodide (1.8g, 12.6 mmol) was added over 2 min. The reaction was stirred for 1 h worked up as above. Recrystallisation from ethyl acetate/ THF (2:1) afforded 2.4 g (91%). The sample was identical in all respects to that described above.

Example 3:

Preparation of 2,7-dibromo-9-(bis-hexylsulfanyl-methylene)fluorene:

A 60% dispersion of sodium hydride in mineral oil (0.26 g, 6.5 mmol) was added under nitrogen to 2,7-dibromofluorene (1.000 g, 3.09 mmol) in anhydrous dimethylsulfoxide (20 mL) at room temperature

with stirring. The reaction mixture was stirred at room temperature for 10 minutes. Carbon disulfide (0.25 g, 0.2 mL, 3.3 mmol) was added *via* syringe and the reaction mixture was stirred at room temperature for 10 minutes. 1-Bromohexane (1.08g, 6.5 mmol) was added and the reaction mixture was stirred at room temperature for 4 h. Ice-water (100 mL) was added and the resulting solid filtered. The crude product was purified by recrystallisation from iso-hexane to afford 1.225 g, (70%) as a bright yellow solid, purity 100% (GC): ^1H and ^{13}C NMR spectra as expected; $M^+ = 568$ (t).

Example 4:

Preparation of 2,7-dibromo-9-(bisdecyl-methylene)fluorene:

To a solution of 2,7-dibromo-9-(bis-methylsulfanyl-methylene) fluorene (10.1g, 23.5 mmol) in dry THF (150 ml) at 0°C under nitrogen, was added a solution of lithium tetrachlorocuprate (5 ml of a 0.1M solution in THF, 2 mol%). A solution of decylmagnesium bromide (52 ml of a 1.0M solution in diethyl ether, 0.052 mol) was added dropwise over 30 min. The reaction was stirred for 2 h, during which time the internal temperature rose to 15°C. The reaction was cooled to 0°C and further lithium tetrachlorocuprate (1 ml of a 0.1M solution in THF, 0.5 mol%) was added. The reaction was stirred a further 2 h, warming to 15°C, before quenching with 5% NaOH (100 ml). The reaction was stirred for 10 min and then filtered through celite. The organic layer was separated and the aqueous layer further washed with ethyl acetate (100 ml). The combined organics were washed with brine (100 ml), dried (sodium sulfate), and concentrated under reduced pressure. The crude oil was further purified by filtration through a plug of silica (5cm x5 cm) covered with a layer of basic alumina (1 cm x 5cm), eluting with petrol. After concentration, eicosane (formed from homocoupling of the Grignard reagent) was removed by distillation at reduced pressure and the residue recrystallised from isohexane to afford 9.75g of the product as white crystals (68%). Purity (HPLC > 98%). ^1H and ^{13}C NMR spectra as expected; $M^+ = 616$ (t).

Example 5:**Preparation of 2,7-dibromo-9-(bis-hexyl-methylene)fluorene:**

5

10

15

To a solution of 2,7-dibromo-9-(bis-methylsulfanyl-methylene)fluorene (5.1g, 12 mmol) in dry THF (80 ml) at 0°C under nitrogen, was added a solution of lithium tetrachlorocuprate (3 ml of a 0.1M solution in THF, 3 mol%). A solution of hexylmagnesium bromide (13 ml of a 2.0M solution in diethyl ether, 0.026 mol) was added dropwise over 30 min. The reaction was stirred for 2 h, during which time the internal temperature rose to 15°C. The reaction was cooled to 0°C and further lithium tetrachlorocuprate (1 ml of a 0.1M solution in THF, 1 mol%) was added. The reaction was then stirred for 24 h at 25°C, before quenching and workup as above. Yield (61%). M.p 47-49°C. ¹H and ¹³C NMR spectra as expected. M⁺ = 504 (t). Anal. Calcd. For C₂₆H₃₂Br₂: C, 61.9; H, 6.4, N, 0.0. Found C, 61.8, H, 6.1, N, <0.3.

20

Example 6:**Preparation of 2,7-dibromo-9-(bis-octyl-methylene)fluorene:**

25

30

35

To a solution of 2,7-dibromo-9-(bis-methylsulfanyl-methylene)fluorene (5.1g, 12 mmol) in dry THF (100 ml) at 0°C under nitrogen, was added a solution of lithium tetrachlorocuprate (5 ml of a 0.1M solution in THF, 5 mol%). A solution of octylmagnesium bromide (13 ml of a 2.0M solution in diethyl ether, 0.026 mol) was added dropwise over 30 min. The reaction was stirred for 2 h at 5°C. The reaction was cooled to 0°C and further lithium tetrachlorocuprate (1 ml of a 0.1M solution in THF, 1 mol%) was added. The reaction was then stirred for 24 h at 15°C, before quenching and workup as above. Yield (60%). Purity (HPLC>99%). ¹H and ¹³C NMR spectra as expected. M⁺ = 560 (t).

Example 7:

Preparation of 2,7-dibromo-9-(bisdodecyl-methylene)fluorene:

To a solution of 2,7-dibromo-9-(bis-methylsulfanyl-methylene)fluorene (4.28, 10 mmol) in dry THF (70 ml) at 0°C under nitrogen, was added a solution of lithium tetrachlorocuprate (2 ml of a 0.1M solution in THF, 2 mol%). A solution of dodecylmagnesium bromide (22 ml of a 1.0M solution in diethyl ether, 0.022 mol) was added dropwise over 15 min. The reaction was stirred for 3 h at 0-5°C before quenching with 5% NaOH (100 ml). The reaction was stirred for 10 min and then filtered through celite. The organic layer was separated and the aqueous layer further washed with ethyl acetate (100 ml). The combined organics were washed with brine (100 ml), dried (sodium sulfate), and concentrated under reduced pressure. The crude oil was further purified by filtration through a plug of silica (5cm x5 cm) covered with a layer of basic alumina (1 cm x 5cm), eluting with petrol. After concentration the residue recrystallised from isohexane to afford 4.2 of the product as white crystals (62%). Purity (HPLC >98%). ¹H and ¹³C NMR spectra as expected.

Example 8:

Preparation of 2,7-dibromo-9-bis(6-methoxyhexyl-methylene)fluorene:


To a solution of 2,7-dibromo-9-(bis-methylsulfanyl-methylene)fluorene (8.60, 20.1 mmol) in dry THF (150 ml) at 0°C under nitrogen, was added a solution of lithium tetrachlorocuprate (10 ml of a 0.1M solution in THF, 5 mol%). A solution of 6-methoxyhexylmagnesium bromide (50 ml of a 1.0M solution in THF, 0.05 mol) was added dropwise over 15 min. The reaction was stirred for 36 h at 20°C before quenching and work-up as described above. Recrystallisation from petrol afforded 8.5 g (75%) of the product. ¹H and ¹³C NMR spectra as expected.

EPO - Munich
67
16 April 2000

Patent Claims

1. Process of preparing a compound of formula I

5




10

by

- a) reacting a compound of formula Ia

15




Ia

20

with a base in the presence of carbondisulfide or a dialkyl trithiocarbonate of the formula [(R'S)₂CS] and an alkylating agent (R'X), and

- b) reacting the resulting compound of formula Ib

25



Ib

30

with a Grignard reagent R¹MgX and/or R²MgX in the presence of a copper catalyst,


35

wherein

- 5 A^1 and A^2 are independently of each other an aromatic 5-ring, 6-ring or 7-ring which optionally contains one or more hetero atoms and is optionally substituted with one or more identical or different groups R,
- R is halogen or has one of the meanings of R^1 ,
- 10 R^1 and R^2 are independently of each other straight chain, branched or cyclic alkyl with 1 to 20 C-atoms, which may be unsubstituted, mono- or poly-substituted by F, Cl, Br, I or CN, it being also possible for one or more non-adjacent CH_2 groups to be replaced, in each case independently from one another, by -O-, -S-, -NH-, - NR^0 -, - SiR^0R^{00} -, -CO-, -COO-, -OCO-, -OCO-O-, - SO_2 -, -S-CO-, -CO-S-, -CH=CH- or -C \equiv C- in such a manner that O and/or S atoms are not linked directly to one another, optionally substituted aryl or heteroaryl, or P-Sp,
- 15 R^0 and R^{00} are independently of each other H or alkyl with 1 to 12 C-atoms,
- 20 P is a polymerisable or reactive group,
- 25 Sp is a spacer group or a single bond,
- X is halogen, and
- 30 R' is straight, branched or cyclic alkyl with 1 to 20 C-atoms, which may be unsubstituted, mono- or poly-substituted by F, Cl, Br, I or CN, it being also possible for one or more non-adjacent CH_2 groups to be replaced, in each case independently from one another, by -O-, -S-, -NH-, - NR^0 -, - SiR^0R^{00} -, -CO-, -COO-, -OCO-, -OCO-O-, - SO_2 -, -S-CO-, -CO-S-, -CH=CH- or -C \equiv C- in such a manner that O
- 35


and/or S atoms are not linked directly to one another, or alkyl aryl with 1 to 20 C-atoms.

2. Process of preparing a compound of formula I1




by

a) reacting a compound of formula I1a



with a base in the presence of carbondisulfide or a dialkyl trithiocarbonate of the formula $[(R'S)_2CS]$ and an alkylating agent $(R'X)$, and

b) reacting the resulting compound of formula I1b




with a Grignard reagent R^1MgX and/or R^2MgX in the presence of a copper catalyst, wherein R^1 , R^2 , R' and X have the meanings given in claim 1,

5 R^3 to R^8 are independently of each other H or have one of the meanings given for R in claim 1, and


R^9 and R^{10} are independently of each other halogen

10 3. Process of preparing a compound of formula I2



by


20 a) reacting a compound of formula I2a



with a base in the presence of carbondisulfide or a dialkyl trithiocarbonate of the formula $[(R'S)_2CS]$ and an alkylating agent $(R'X)$, and

30 b) reacting the resulting compound of formula I2b

35



12b

with a Grignard reagent R^1MgX and/or R^2MgX in the presence of a copper catalyst, wherein R^1 , R^2 , R' and X have the meanings given in claim 1,

R^3 to R^4 are independently of each other H or have one of the meanings given for R in claim 1, and

R^9 and R^{10} are independently of each other H or halogen.

4. Process according to at least one of claims 1 to 3, characterized in that the alkylating agent in step a) is an alkylhalogenide or alkyl aryl halogenide of formula $R'X$, wherein X is Cl, Br or I and R' is alkyl or alkyl aryl with 1 to 15 C-atoms.
5. Process according to at least one of claims 1 to 4, characterized in that the base in step a) is selected from NaH, KOH, NaOtbut and KOtbut.
6. Process according to at least one of claims 1 to 5, characterized in that the copper catalyst in step b) is Li_2CuCl_4 .
7. Process according to at least one of claims 1 to 6, characterized in that the Grignard reagent in step b) is R^1MgX wherein X is Cl, Br or I.
8. Process according to at least one of claims 1 to 7, characterized in that A^1 and A^2 are benzene, thiophene or pyridine.
9. Process according to at least one of claims 1 to 8, characterized in that R^1 and R^2 are selected from C_1 - C_{20} -alkyl that is optionally

substituted with one or more fluorine atoms, C₁-C₂₀-alkenyl, C₁-C₂₀-alkynyl, C₁-C₂₀-alkoxy, C₁-C₂₀-thioalkyl, C₁-C₂₀-silyl, C₁-C₂₀-ester, C₁-C₂₀-amino, C₁-C₂₀-fluoroalkyl, or optionally substituted aryl or heteroaryl.

5

10. Process according to at least one of claims 1 to 9, characterized in that R⁹ and R¹⁰ are Cl, Br or I.

10

11. Compounds of formula I, I1, I2, Ib, I1b or I2b obtainable by a process, or by step a) thereof, according to at least one of claims 1 to 10.

15

20

25

30

35

Abstract of the Disclosure

The invention relates to a process of preparing disubstituted 9-alkylidene fluorenes and structure analogous compounds, to novel compounds and intermediates prepared by this process, their use for the preparation of conjugated polymers and copolymers thereof, and to novel polymers and copolymers thereby prepared.

THIS PAGE BLANK (USPTO)